

## Effect of crystallinity and morphology on the electrical properties of $Y_2O_3$ thin films prepared by pulsed laser deposition for MOSFET

S. K. Suresh Babu<sup>1,2</sup>, A. Youvanidha<sup>1</sup>, D. Jackuline Moni<sup>2\*</sup>, S. Divya<sup>1</sup>

<sup>1</sup> Department of Nanoscience, Karunya Institute of Technology and Sciences, Coimbatore, India.

<sup>2</sup> Department of Electronics and Communication Engineering, Karunya Institute of Technology and Sciences, Coimbatore, India.

### ABSTRACT

*The paper focuses on the effect of the crystalline structure and surface morphology on the electrical properties of Yttrium oxide ( $Y_2O_3$ ) thin films. The impact on the change in substrate temperature from ambient to 650°C in low oxygen pressure (0.0034mbar) was realised by change in crystallinity and morphology. The XRD result shows the preferred orientation along the (400) plane. The effect of substrate temperature on the crystal structure has been studied and the same impact has been observed in film morphology using scanning electron microscopy. The higher dielectric constant of 21 was observed at room temperature deposition. The transfer characteristic of  $Y_2O_3$  gate dielectric based Si-MOSFET gives current ratio  $I_{ON}/I_{OFF}$  of  $10^7$  and threshold voltage of -2.8V. Furthermore, from output characteristics, the obtained  $I_{DSS}$  is 0.415 mA. The high  $I_{ON}/I_{OFF}$ , makes it suitable for digital gates, optical electronics, SMPS and portable electronic applications.*

**Keywords:** Yttrium oxide, pulsed laser deposition, crystalline structure, Field effect transistor, high-k gate dielectric.

### 1. INTRODUCTION

Silicon dioxide ( $SiO_2$ ), a prominent dielectric material in semiconductor devices exhibits a dielectric constant of only 3.5 [1- 3]. It has been reported that rare earth oxide films such as  $Eu_2O_3$ ,  $Y_2O_3$  etc., are found to exhibit excellent dielectric properties with reproducible results [4]. These high-k dielectric materials unlike  $SiO_2$  could help in tuning the thickness of gate dielectric to prevent tunnelling, resulting in reduced leakage current [5-7] Among these,  $Y_2O_3$  being the most available rare earth oxide deposited on Si substrate have gained much attention in recent years [4,6]. The significant properties of  $Y_2O_3$  include its thermal & chemical stability, low leakage current, wide band gap (5eV) and relatively high dielectric constant (14 ~ 18) with respect to  $SiO_2$  [8-11].

Several deposition techniques have been reported to fabricate  $Y_2O_3$  thin films, which includes sputtering [12], molecular beam epitaxy [13], electron beam deposition [14], chemical vapour deposition [15] and pulsed laser deposition (PLD). Among these PLD is reported to have excellent stoichiometry transfer with low cost and high deposition rate [16-18]. It has been reported that the texture of film varies with the change in oxygen pressure and/or temperature of the substrate [19-20]. It has to be noted that when the substrate temperature is higher, the atoms get enough time to arrange in the low energy stable structure due to the increase in mobility of adatoms [21]. This is again supported by the low oxygen pressure, where the collision between the ablated species and oxygen atom is less probable and so the ablated species get enough time to form the low energy structure [21].

moni@karunya.edu

Several oxide materials deposited by PLD at different substrate temperatures and oxygen partial pressure have been tested for its properties [22, 23]. For  $\text{TiO}_2$  it has been reported that the films deposited below  $1 \times 10^{-4}$  mbar oxygen pressure exhibited an amorphous nature, whereas for the pressure between  $1 \times 10^{-4}$  to  $1 \times 10^{-2}$  mbar these films were of crystalline nature [22-24]. For  $\text{CoO}$  film two oxidation processes have been reported to take place during the film growth in PLD. Direct oxidation takes place during film deposition for  $\text{O}_2$  pressure higher than  $1 \times 10^{-3}$  mbar. This was followed by surface oxidation which occurred after the deposition. In order to avoid the formation of  $\text{CO}_3\text{O}_4$  and protect the film a Pt over layer has been used [23]. Therefore from the previous literature we observe that the oxygen partial pressure is material dependant and it plays a significant role in determining the properties of the deposited film.

$\text{Y}_2\text{O}_3$  thin films deposited by PLD Shaoqiang Zhang et.al. [25] Have observed the formation of amorphous film with the increase in oxygen pressure from (0.0001mbar to 0.1 mbar) at a fixed temperature of  $650^\circ\text{C}$ . Similar observation has been made by Mishra et.al. [21], where they have reported a decrease in crystalline size of pulsed laser deposited  $\text{Y}_2\text{O}_3$  thin films with the increase in oxygen pressure from 0.00002 mbar to 0.02 mbar. Also they have observed an increase in crystallinity with the increase in substrate temperature.

It is clear from the above reports that  $\text{Y}_2\text{O}_3$  can be deposited both in crystalline and amorphous form by tuning the partial pressure and substrate temperature. At the same time as discussed above in order to attain stable low energy structure we have to maintain high temperature and low pressure. Based on the previous reports in the present work, we have focused on the deposition of  $\text{Y}_2\text{O}_3$  at a wide range of substrate temperature from room temperature to  $650^\circ\text{C}$  and low oxygen partial pressure of 0.0034mbar, which is within the range reported in previous literature [21,24]. We have reported the effect of these parameters on the structure, morphology and dielectric properties of the Pulsed Laser Deposited  $\text{Y}_2\text{O}_3$  films [26-28]. Further the previous reports were based on the crystallinity of the deposited films, here we have also focussed on the difference in morphology of the film which had an impact on its electrical properties. The film deposited with low resistivity and high dielectric constant has been used in the fabrication of FET and the device characteristics were studied.

## 2. EXPERIMENTAL

Yttrium Oxide ( $\text{Y}_2\text{O}_3$ ) source material with 99.9% purity has been used for the depositions. The high power pulsed laser (Nd-YAG laser) is focused to  $\text{Y}_2\text{O}_3$  pellet target which is placed inside the vacuum chamber. The PLD system consists of 8 target rotating holder in one side of the chamber and on the other side it consists of substrate holder with a controlled heater. Various quartz windows are mounted to check the position of target and substrate. The laser beam passed through quartz window and hit the target. The chamber was evacuated by rotary and turbo pumps and then oxygen was supplied from the cylinder to maintain the required oxygen partial pressure.


N-Type Silicon substrate with (110) orientation, resistivity of 0.001 ohms-cm and dimension of 1cm X 1cm been used for the deposition of  $\text{Y}_2\text{O}_3$  [28]. The deposition has been carried out with a

fixed and low oxygen pressure (0.0034 mbar) and different substrate temperatures. The temperature was noted by setting temperature of substrate heater, which is in built system controlled by PID controller. (Room temperature, 250°C, 450°C and 650°C).

Various characterization techniques have been employed to study the properties of the deposited  $Y_2O_3$  films. The characterization techniques include X-ray diffraction (XRD-SHIMADZU model XRD-6000) to study the crystalline structure, Scanning Electron Microscope (SEM-JOEL model JSM-6390) for the study of film morphology. The surface continuity of the film has been studied using AFM (Multiview 2000 – Nanonics). The dielectric constant has been measured using Solatron 1260 impedance analyser. The thickness of the film was measured by using dehta-kXT stylus profilometer from Bruker. The output characterization of the fabricated FET was measured using National Instrument PXI-4100 I-V source meter.

### 3. RESULTS AND DISCUSSION


The XRD patterns of  $Y_2O_3$  films deposited with different substrate temperatures ( $T_s$ ) as Room temperature, 250°C, 450°C & 650°C are shown in Figure 1. The deposited film at room temperature shows a broad diffraction pattern without any preferential orientation, which indicates the amorphous or nano-crystalline nature of the films.




**Figure 1.** XRD pattern of  $Y_2O_3$  deposited thin films at various deposition temperatures in PLD chamber

With the increase in substrate temperature from 250°C, 450°C and 650°C, the films exhibited a diffraction peak with preferential orientation along the (400) plane according to (ICDD file no. 44-0399) [29], the crystal structure has been identified to be monoclinic, which is in agreement with the reported results [29]. These results are in agreement with the previous reports by Shaoqiang Zhang et al. [24]. They have reported a preferential orientation along (222) plane with a relatively high  $O_2$  partial pressure maintained at 0.01mbar. Also they have reported the emergence of (400) peak with a further increase in oxygen partial pressure from 0.05mbar to 0.1mbar. In the present work, we have attained similar orientation along (400) plane under low oxygen partial pressure condition of 0.0034mbar, which ensures the formation of stable structure of  $Y_2O_3$  at low pressure.

The SEM image obtained for the films deposited at various substrate temperatures is shown in Figure 2. It is clear from the image that  $Y_2O_3$  thin film deposited at room temperature showed slightly porous nature with loosely packed particles, which could have been the reason for the broad XRD pattern as well. With the increase in substrate temperature it is evident that the particles started to coalesce and merge with each other, as evident in Figure 2 C, where two particles are connected to each other. With further increase in temperature to 450°C the particles have further decreased in size and some widely distributed nucleation sites are evident. For the substrate-temperature of 650°C many new crystallites with nano size are evident, which would be the reason for broad peak in XRD of this film, but the particles are still determined to have a preferential growth along the (400) plane





**Figure.2** SEM image of  $Y_2O_3$  at various deposition temperature (a) Room temperature (b) 250°C (c) 450°C and (d) 650°C

Using solatron 1260, the capacitance study was carried out for the Metal Oxide Semiconductor (MOS) structure of  $Y_2O_3$  films at various substrate temperatures which is shown in Figure 3. The capacitance (C) equals 312nf, 267nf, 264nf and 265nf were obtained for various substrate temperatures of room temperature, 250°C, 450°C and 650°C respectively at 50HZ to 1MHZ of applied frequency. The dielectric constant (k) of the films was calculated from the parallel plate capacitance equation eq.1 which is shown below [25][30]. By rearranging eq.1, the dielectric



constant k has been obtained from the eq.2 [25]

**Figure 3.** Capacitor structure with  $Y_2O_3$  thin film

Where  $\epsilon$  is the constant dielectric permittivity at vacuum, area (A) of film was 1cm X 1cm and the thickness (d) of the deposited  $Y_2O_3$  film was 61 nm. Thickness of the  $Y_2O_3$  thin film was measured as 61nm by using stylus profilometer.

Where  $\epsilon$  is the constant dielectric permittivity at vacuum, area (A) of film was 1cm X 1cm and the thickness (d) of the gate dielectric was measured by stylus profilometer as 61nm. The dielectric constant for various substrate temperature of the film was calculated and tabulated in **Table 1.**


$$C = \frac{k \cdot \epsilon \cdot A}{d} \quad (1)$$

$$k = \frac{c \cdot d}{\epsilon \cdot A} \quad (2)$$

**Table 1.** Dielectric constant values of  $Y_2O_3$  thin film at various temperatures


Substrate Temperature	Dielectric Constant (k)
Room temperature	21
250°C	19
450 °C	17
650°C	18

From these results, it is observed that the dielectric constant of  $Y_2O_3$  film gradually decreases with the increase in substrate temperature and also there is a sudden increase in the dielectric constant for the film deposited at substrate temperature of 650°C which is in accordance with the results observed in XRD and SEM of various substrate temperature deposited films. Among these high orders dielectric constant was observed at room temperature. With these XRD, SEM and electrical studies;  $Y_2O_3$  film deposited at room temperature can be used preferably for field effect transistor as gate dielectric layer due to its high value of dielectric constant than the other deposited films. In order to further ensure the continuity of the film, AFM images were taken for the room temperature deposited film as shown in figure 4, before it could be used in the fabrication of FET.

**Figure 4.** AFM image of pulsed laser deposited  $Y_2O_3$  film at room temperature

#### 4. MOSFET FABRICATION AND ELECTRICAL CHARACTERISTICS


The step by step fabrication process of MOSFET is shown in Figure 5. The device fabrication starts up by taking a well cleaned and processed N-type Silicon (Si) wafer chosen as channel and also a base layer of FET.



**Figure 5.** Fabrication steps involved for the proposed Y<sub>2</sub>O<sub>3</sub> gate dielectric Si-MOSFET


The Y<sub>2</sub>O<sub>3</sub> film was deposited as the gate dielectric 61nm at room temperature over silicon by using PLD. This deposition was carried out with fixed O<sub>2</sub> pressure (0.0034mbar) and pulse laser repetition rate at 10Hz. Using the prepared mask the drain, source & gate electrode are deposited using gold (Au) by DC sputtering. The electrical characterization of the film has been carried out using National Instruments PXI 4110.

The output I-V characteristics of the Y<sub>2</sub>O<sub>3</sub> based gate dielectric of MOSFET is shown in Figure 6. I-V characteristic were analysed by varying the drain source voltage ( $V_{DS}$ ) between 0 to 6 volts with constant increment of -2 volts of gate source voltages ( $V_{GS}$ ) between 0V to -6V. The output current  $I_D$  is obtained in the range of milliamps.



**Figure 6.** Output characteristics of n-channel MOSFET with  $Y_2O_3$  used as a gate dielectric


This output response shows n-channel FET with ohmic and saturation region in the characteristics curve. The output current drain current ( $I_D$ ) is reduced with the increase in the negative gate voltage, which is observed in the principle of depletion FET. These results clearly show the output current is controlled by input gate voltage ( $V_G$ ). From Figure 6 we observed  $I_{dss}$  (drain current at  $V_{GS}=0V$ ) as 0.415 mA. This  $I_{dss}$  is the maximum drain current which reaches without the restricted breakdown region. It is also referred as the drain current for zero biasing voltage.



**Figure 7.** Transfer characteristics of n-channel MOSFET with  $Y_2O_3$  used as a gate dielectric



Transfer characteristics of  $Y_2O_3$  thin film transistor is shown in Figure 7, the obtained output drain current for the applied input by gate voltage ( $V_{GS}$ ) ranging between -3 to 2V at different constant voltages  $V_{DS}$  (1V, 2V, 4V and 6V). The result clearly shows output drain current gradually increases with the increase in gate voltage as per the depletion N-channel MOSFET principle with control of applied  $V_{DS}$ .



**Figure 8.** Logarithmic and square root of output drain current Vs gate voltage at  $V_{DS}=6V$

The various electrical parameters like  $I_{DSS}$ , threshold voltage and  $I_{ON}/I_{OFF}$  calculations analysed for the  $V_{DS}$  at 6V is shown in Figure 8. The threshold voltage -2.8 V was attained from the extrapolation of the square root of drain current ( $I_D$ ) to the gate voltage ( $V_{GS}$ ) [32] and  $I_{ON}/I_{OFF}$  ratio is obtained from the logarithmic value of drain current to gate voltage as  $10^7$  [31]. This value has been reported as  $10^6$  Liu A et.al.[32] and Song K et.al.[33]. The obtained results show that less leakage current was achieved in the fabricated MOSFET.

## 5. CONCLUSION

In this paper  $Y_2O_3$  thin films were deposited at different substrate temperatures using pulsed laser deposition and their characterization studies have been carried out. These studies show that the  $Y_2O_3$  thin film exhibits amorphous nature when there is no substrate temperature. But it exhibits crystalline peak when the temperature is applied from 250°C to 650°C and also it observed that at 650°C film exhibited a diffraction peak resembling the room temperature deposited film but with the preferential orientation maintained along (400) plane. In I-V characterization of films, the high resistance effect was observed at room temperature deposited film with a high dielectric constant of 21. The fabrication of FET has been carried out with N-Channel silicon with  $Y_2O_3$  film (room temperature deposited) as a gate dielectric material of FET.  $I_{DSS}$  of 0.415 mA, threshold voltage ( $V_{TH}$ ) of -2.8V and  $I_{ON}/I_{OFF}$  ratio of  $10^7$  were obtained for fabricated device.

## REFERENCES:

- [1] Wang, J., Xiong, Y., Wang, D., & Liu, H. (2011). Study on preparation and characters of one multi-function SiO<sub>2</sub> film. *Physics Procedia*, 18, 143-147.
- [2] Hirose, K., Nohira, H., Koike, T., Aizaki, T., & Hattori, T. (1998). Initial stage of SiO<sub>2</sub> valence band formation. *Applied surface science*, 123, 542-545.
- [3] Nafria, M., Sune, J., & Aymerich, X. (1996). Breakdown of thin gate silicon dioxide films— A review. *Microelectronics Reliability*, 36(7-8), 871-905.
- [4] Peeva, A., Dikovska, A. O., Atanasov, P. A., de Castro, M. J., & Skorupa, W. (2007). Rare-earth implanted Y<sub>2</sub>O<sub>3</sub> thin films. *Applied surface science*, 253(19), 8165-8168.
- [5] Ambikeswari, N., & Manivannan, S. (2018). Effect of reaction time on the dielectric behaviour of reduced graphene oxide-layered cobalt hydroxide composite for high-k gate dielectrics. *Materials Research Bulletin*, 100, 7-14.
- [6] Walker, B., Pradhan, A. K., & Xiao, B. (2015). Low temperature fabrication of high performance ZnO thin film transistors with high-k dielectrics. *Solid-State Electronics*, 111, 58-61.
- [7] Baidya, A., Baishya, S., & Lenka, T. R. (2017). Impact of thin high-k dielectrics and gate metals on RF characteristics of 3D double gate junctionless transistor. *Materials Science in Semiconductor Processing*, 71, 413-420.
- [8] Krawczyk, M., Lisowski, W., Pisarek, M., Nikiforow, K., & Jablonski, A. (2018). Surface characterization of low-temperature grown yttrium oxide. *Applied Surface Science*, 437, 347-356.
- [9] Hou, X., Zhou, S., Li, W., & Li, Y. (2010). Study on the effect and mechanism of zirconia on the sinterability of yttria transparent ceramic. *Journal of the European Ceramic Society*, 30(15), 3125-3129.
- [10] Barve, S. A., Mithal, N., Deo, M. N., Chand, N., Bhanage, B. M., Gantayet, L. M., & Patil, D. S. (2010). Microwave ECR plasma CVD of cubic Y<sub>2</sub>O<sub>3</sub> coatings and their characterization. *Surface and Coatings Technology*, 204(20), 3167-3172.
- [11] Jinqing, C. H. E. N., HUANG, B., HUANG, C., & Xiaoqi, S. U. N. (2017). Preparation of nanoscaled yttrium oxide by citrate precipitation method. *Journal of Rare Earths*, 35(1), 79-84.
- [12] Xiong, J., Xia, Y., Xue, Y., Zhang, F., Guo, P., Zhao, X., & Tao, B. (2014). Development of mid-frequency AC reactive magnetron sputtering for fast deposition of Y<sub>2</sub>O<sub>3</sub> buffer layers. *Physica C: Superconductivity and its Applications*, 497, 38-42.
- [13] TANG, M. H., ZHOU, Y. C., ZHENG, X. J., Zhi, Y. A. N., CHENG, C. P., Zhi, Y. E., & HU, Z. S. (2006). Characterization of ultra-thin Y<sub>2</sub>O<sub>3</sub> films as insulator of MFISFET structure. *Transactions of Nonferrous Metals Society of China*, 16, s63-s66.
- [14] Cho, M. H., Ko, D. H., Seo, J. G., Whangbo, S. W., Jeong, K., Lyo, I. W., ... & Kim, H. J. (2001). Characteristics of Y<sub>2</sub>O<sub>3</sub> films on Si (111) grown by oxygen-ion beam-assisted deposition. *Thin Solid Films*, 382(1-2), 288-296.
- [15] Goto, T., Banal, R., & Kimura, T. (2007). Morphology and preferred orientation of Y<sub>2</sub>O<sub>3</sub> film prepared by high-speed laser CVD. *Surface and Coatings Technology*, 201(12), 5776-5781.
- [16] Mudavakkat, V. H., Atuchin, V. V., Kruchinin, V. N., Kayani, A., & Ramana, C. V. (2012). Structure, morphology and optical properties of nanocrystalline yttrium oxide (Y<sub>2</sub>O<sub>3</sub>) thin films. *Optical Materials*, 34(5), 893-900.

- [17] Burmester, P. B. W., Ishii, T., Huber, G., Kurfiss, M., & Schilling, M. (2003). Characterization of crystalline europium doped  $\alpha$ -Y<sub>2</sub>O<sub>3</sub> PLD-films grown on  $\alpha$ -Al<sub>2</sub>O<sub>3</sub>. *Materials Science and Engineering: B*, 105(1-3), 25-29.
- [18] Dikovska, A. O., Atanasov, P. A., Tomov, R. I., Tonchev, S. H., & Sapundjiev, D. T. (2002). Er: Y<sub>2</sub>O<sub>3</sub> thin films grown by pulsed laser deposition. *Vacuum*, 69(1-3), 273-276.
- [19] Bassim, N. D., Schenck, P. K., Donev, E. U., Heilweil, E. J., Cockayne, E., Green, M. L., & Feldman, L. C. (2007). Effects of temperature and oxygen pressure on binary oxide growth using aperture-controlled combinatorial pulsed-laser deposition. *Applied Surface Science*, 254(3), 785-788.
- [20] Salem, E. T., Ismail, R. A., Fakhry, M. A., & Yusof, Y. (2016). Reactive PLD of ZnO thin film for optoelectronic application. *International Journal of Nanoelectronics & Materials*, 9(2).
- [21] Mishra, M., Kuppusami, P., Sairam, T. N., Singh, A., & Mohandas, E. (2011). Effect of substrate temperature and oxygen partial pressure on microstructure and optical properties of pulsed laser deposited yttrium oxide thin films. *Applied Surface Science*, 257(17), 7665-7670.
- [22] Kunti, A. K., Sekhar, K. C., Pereira, M., Gomes, M. J. M., & Sharma, S. K. (2017). Oxygen partial pressure induced effects on the microstructure and the luminescence properties of pulsed laser deposited TiO<sub>2</sub> thin films. *AIP advances*, 7(1), 015021.
- [23] Devi, M., & Panigrahi, M. R. (2017). Effect of annealing temperature on the optical and electrical properties of Mg doped TiO<sub>2</sub> thin films. *International Journal of Nanoelectronics & Materials*, 10(1).
- [24] Laureti, S., Agostinelli, E., Scavia, G., Varvaro, G., Albertini, V. R., Generosi, A., ... & Kaciulis, S. (2008). Effect of oxygen partial pressure on PLD cobalt oxide films. *Applied Surface Science*, 254(16), 5111-5115.
- [25] Zhang, S., & Xiao, R. (1998). Yttrium oxide films prepared by pulsed laser deposition. *Journal of applied physics*, 83(7), 3842-3848.
- [26] Grove, T. T., Masters, M. F., & Miers, R. E. (2005). Determining dielectric constants using a parallel plate capacitor. *American journal of physics*, 73(1), 52-56.
- [27] Kurilchik, S., Grant-Jacob, J., Prentice, J., Hua, P., Eason, R., & Mackenzie, J. (2018). Pulsed-laser-deposited Yb: YAG planar-waveguide amplifier.
- [28] Korzenski, M. B., Lecoœur, P., Mercey, B., Chippaux, D., Raveau, B., & Desfeux, R. (2000). PLD-grown Y<sub>2</sub>O<sub>3</sub> thin films from Y metal: An advantageous alternative to films deposited from yttria. *Chemistry of materials*, 12(10), 3139-3150.
- [29] Yu, P., Zhang, K., Huang, H., Wen, M., Li, Q., Zhang, W., ... & Zheng, W. (2017). Oxygen vacancies dependent phase transition of Y<sub>2</sub>O<sub>3</sub> films. *Applied Surface Science*, 410, 470-478.
- [30] Alarcon-Flores, G., Aguilar-Frutis, M., Falcony, C., García-Hipolito, M., Araiza-Ibarra, J. J., & Herrera-Suárez, H. J. (2006). Low interface states and high dielectric constant Y<sub>2</sub>O<sub>3</sub> films on Si substrates. *Journal of Vacuum Science & Technology B: Microelectronics and Nanometer Structures Processing, Measurement, and Phenomena*, 24(4), 1873-1877.

- [31] Kaushik, V. K., Mukherjee, C., Ganguli, T., & Sen, P. K. (2017). Electrical and optical characteristics of aerosol assisted CVD grown ZnO based thin film diode and transistor. *Journal of Alloys and Compounds*, 696, 727-735.
- [32] Liu, A., Liu, G., Zhu, H., Meng, Y., Song, H., Shin, B., ... & Shan, F. (2015). A water-induced high-k yttrium oxide dielectric for fully-solution-processed oxide thin-film transistors. *Current Applied Physics*, 15, S75-S81.
- [33] Song, K., Yang, W., Jung, Y., Jeong, S., & Moon, J. (2012). A solution-processed yttrium oxide gate insulator for high-performance all-solution-processed fully transparent thin film transistors. *Journal of Materials Chemistry*, 22(39), 21265-21271.